



Richlite Company  
 624 E. 15th Street  
 Tacoma, WA 98421  
 info@richlite.com

**Properties of Richlite, Natural Fiber Composite**

Electrical Properties	
Dielectric Strength (Volts/mil).....	150
Dielectric Constant.....	9.24
Disipation Facto.....	0.29
Thermal Properties	
Coeff. Of Thermal Expansion In X Dir (min/in.∞F).....	5.2
Coeff of Thermal Expansion In Y Dir (min/in.∞F).....	12.8
Coeff of Thermal Expansion In Z Dir (min/in.∞F).....	45.9/73.5”
Thermal Conductivity (Cal cm/cm2 sec ∞C).....	0.00051
Tensile Strength	
X Direction(psi).....	19,200
Y Direction (psi).....	13,100
Compressive Strength	
X Direction (psi).....	18,400
Strain @ Failure.....	7.09%
Y Direction (psi).....	15,900
Strain @ Failure.....	7.15%
Z Direction (psi).....	30,000
Strain @ Failure.....	~20%
Flexural Strength (Face In Tension)	
X Direction (psi).....	22,000
Y Direction (psi).....	17,300
Flexural Strength (Edge In Tension)	
X Direction (psi).....	20,400
Y Direction (psi).....	16,100
Izod Impact (Face Impact)	
X Direction (ft. lb. Per Inch of width).....	2.48
Y Direction (ft. lb. Per Inch of width).....	1.46
Izod Impact (Edge Impact)	
X Direction (ft. lb. Per Inch of width).....	0.68
Y Direction (ft. lb. Per Inch of width).....	0.62
Abrasion Resistance – Taber Abraser (CS-17) (1/4x”x4”x4”)	
Weight Loss per 1000 revs.....	0.0112%
Wear per 1000 revs (Inches).....	0.00011
Coefficient of Friction (Unpolished).....	0.2
Burning Rate.....	Very Slow
Aging.....	Improves Mechanical and Electrical Properties
Sunlight.....	Darkens Surface
Clarity.....	Opaque
Weak Acids.....	None to slight depending on Acid
Strong Acids.....	None to slight for reducing and organic
Decomposed by oxidizing acids	
Weak Alkali.....	Slight to marked depending on alkalinity
Strong Alkali.....	Decomposes
Organic Solvents.....	None
Metal Inserts.....	Inert

“The two values for C.O.L.T.E. represent coefficients below and above glass transition temperature (130∞F) respectively.